

Patent Claims

1. A mixture of powders suitable for preparation of absorbable calcium phosphate cements comprising:
- 5 ✓ tricalcium phoshate (TCP) in which,
 -30 to 70% of the TCP particles have a particle size of 0.1 to 7um and
 -10 to 60% of the TCP particles have a particle size of 40 to 100 um;
- 10 precipitated hydroxylapatite (PHA) wherein the PHA is a cation-deficient hydroxylapatite of the formula I
$$\text{Ca}_{8.75}\text{V}(\text{Ca})_{1.25}[(\text{HPO}_4)_{5.5-x}(\text{CO}_3)_{0.5}](\text{OH})_x\text{V}(\text{OH})_{2-x}$$
 in which x is 0-2 ;and
- 15 at least one other phosphate -containing inorganic compound.
2. A mixture according to claim 1, wherein said mixture after hardening has a compressive strength of
- 20 between 70 - 80 Mpa.
3. A mixture according to claim 1, wherein the PHA has a particle size of 0.5- 10 um.
- 25 4. A mixture according to claim 3, wherein the PHA has a particle size of 0.5 - 5 um.
5. A mixture according to claim 1, wherein the PHA content is from 1 - 5% by weight, based on the total
- 30 dry mass.
6. A mixture according to claim 1, wherein the PHA content is from 1.7 - 2.7 % by weight, based on the total dry mass.
- 35 7. A mixture according to claim 1, wherein said at least one other phosphate-containing inorganic compound is selected from CaHPO_4 , carbonate-containing apatite and CaCO_3 .

35

SUB

B2

8. A mixture according to claim 1, additionally comprising a setting accelerator.

5 9. A mixture according to claim 1, additionally comprising a pharmaceutically active ingredient.

10 10. A mixture according to claim 9, wherein said pharmaceutically active ingredient is an antibiotic or disinfectant.

11. A mixture according to claim 1, present in the form of an aqueous solution, suspension or paste.

15 12. A biodegradable implant produced from a hardened mixture according to claim 11.

20 13. A method of preparing biodegradable implantable synthetic bone materials comprising, hardening a mixture according to claim 1.

25 14. A mixture according to claim 9, wherein said pharmaceutically active ingredient is a growth factor or a prostaglandin.

30 15. A mixture according to claim 14, wherein said growth factor is a bone morphogenic protein, a tissue growth factor, a fibroblast growth factor, or a growth factor from the TGF β superfamily.

16. An absorbable calcium phosphate cement paste comprising cement powders according to claim 1, and a liquid phase.

35 17. A kit for the preparation of a bio-cement paste comprising a mixture of powders according to claim 1, a pharmaceutical active ingredient and a liquid phase.

18. A method of preparing a precipitated hydroxylapatite (PHA) comprising:

homogenously mixing CaSO_4 , Na_3PO_4 , CaCO_3 in an aqueous solution;

dissolving at least one magnesium salt into aqueous solution;

removing resultant precipitate and

washing with a neutral electrolyte.

19. A method according to claim 18, in which the magnesium salt is magnesium chloride, magnesium sulfate, magnesium nitrate or one or more of their hydrates.

20. A method of repairing bone fractures comprising applying an absorbable calcium phosphate paste according to claim 16, to a bone fracture.

add
C1

add
B3

SUB
B2

TOP SECRET